

Resilient floorcovering for rail vehicle		
<p>Based on plasticized polymers, it combines safety, flexibility & durability</p> <p>The Glass Fiber Web provides an outstanding dimensional stability</p> <p>The Non-woven textile backing in PES improves the bonding properties.</p> <p>The ProtecSol surface treatment enables an easy cleaning.</p>		
Roll width	150 cm	
Roll length	12-24 lm	
Technical Information		
Total thickness	ISO 24346	2,50 ± 0,15 mm
Weight per sqm	ISO 23977	2,94 ± 0,15 kg
Dimensional stability (6h @ 80°C)	ISO23999	≤0,3%
Abrasion resistance	ISO 9352	< 300 mg
Slip resistance	EN16165 - Annex B	R10
Flexibility	EN ISO 24 344 Procedure A	Ø 8mm - No cracks
Indentation Resistance	ISO 24343-1	Mean value ≤ 0,15 mm average ~ 0,10
Low Temperature Resistance Impact test	D42 1235 A	No cracks at -20°C
Impact Phonic insulation	ISO 10140-3 / ISO 717-2	5dB
Colour fastness	ISO 105-B02	>6 vs Grey scale n°4
Fire resistance	EN45545-2	HL2
Resistance to chemicals	ISO 26987 :2012	Unaffected by domestic products excluding solvents for plasticized PVC
Indoor air quality		
TVOC after 28 days(µg/m3)	ISO 16000-6	<1000